Book Chapter

The Role of Gangue Mineralogy on Flowsheet Development in Fluorite Processing

Jestos Taguta^{1*}, Kebone Carol Teme² and Portia Ngobeni¹

¹Mineral Processing Division, Mintek, South Africa

²Jubilee Metals Group, South Africa

***Corresponding Author:** Jestos Taguta, Mineral Processing Division, Mintek, Private Bag X3015, Randburg 2125, South Africa

Published **July 09, 2020**

This Book Chapter is a republication of an article published by Jestos Taguta, et al. at Minerals in March 2020. (Taguta, J.; Teme, K.C.; Ngobeni, P. The Role of Gangue Mineralogy on Flowsheet Development in Fluorite Processing. Minerals 2020, 10, 237.)

How to cite this book chapter: Jestos Taguta, Kebone Carol Teme, Portia Ngobeni. The Role of Gangue Mineralogy on Flowsheet Development in Fluorite Processing. In: Arkady Kalinin, editor. Minerals: Technology and Advances. Hyderabad, India: Vide Leaf. 2020.

© The Author(s) 2020. This article is distributed under the terms of the Creative Commons Attribution 4.0 International License(<http://creativecommons.org/licenses/by/4.0/>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Acknowledgments: The authors would like to acknowledge Mintek's commercial clients for granting the permission to publish information gained from the testwork. Support from the

Mineral Processing Division's technical team at Mintek is greatly appreciated.

Author contributions: Jestos Taguta, Kebone Carol Teme and Portia Ngobeni conceived the research idea and designed the experiments; Kebone Carol Teme and Portia Ngobeni conducted the experiments; Jestos Taguta, Kebone Carol Teme and Portia Ngobeni analysed the results; Jestos Taguta interpreted the data; Jestos Taguta wrote the paper.

Conflict of Interest: The authors declare no conflict of interest.

Abstract

Fluorite, CaF_2 , is considered a strategically important mineral as it is a raw material for many strategic industries. Froth flotation is reported to be the most efficient and economically viable process for the production of an acid grade product with a CaF_2 content of at least 97%. Selective flotation of fluorite from gangue minerals, e.g. calcite and barite is challenging because these minerals have similar physicochemical properties. This study employed batch flotation tests coupled with mineralogical analysis to design suitable customised flowsheet and efficiently optimised reagent regimes for optimum production of acid-grade fluorite concentrate from 2 different fluorite ores by the froth flotation process. Some fluorite processing plants are located in northern China which is characterised by long cold winters necessitating thermal heating of the ore slurry translating to high energy costs. The effect of pulp temperature on fluorite flotation were therefore investigated in this study with the objective of lowering pulp temperatures in fluorite flotation.

The results showed that an acid-grade CaF_2 concentrate could be obtained from the flotation of both ores at ambient pulp temperatures. This eliminates the requirement for high-temperature pulp treatment which would result in significant reduction in thermal energy costs. This study showed that an understanding of gangue mineralogy is key to process optimisation for acid grade CaF_2 production. Although an acid grade CaF_2 concentrate could be produced from both ores, the

flowsheets and reagent regimes were markedly different. For instance, the production of an acid-grade CaF_2 product from a high quartz and calcite ore was achieved by employing a simple rougher-multiple cleaner flotation circuit using tannin and sodium silicate as calcite and quartz depressants respectively. On the other hand, the production of an acid-grade CaF_2 product from the flotation of the pyritic ore required a pre-sulphide flotation stage for upfront sulphur removal and the use of sulphide depressant. Multiple stages of cleaning were required for improved selectivity in the flotation of both ores.

Keywords

Froth Flotation; Fluorite; Selectivity; Depressant; Gangue; Mineralogy

Introduction

Fluorite, CaF_2 , is considered a strategically important mineral that is used in the production of hydrofluoric acid and as a flux agent in the steel making industry. Fluorite ores are beneficiated through different techniques, viz: froth flotation, gravity and magnetic concentration depending on the end use of the fluorite. Froth flotation is reported to be the most efficient and economically viable process for the production of an acid grade product with a CaF_2 content of at least 97%.

The mineralogical compositions of current fluorite deposits are becoming increasingly complex, making the selective flotation of fluorite from gangue even more challenging. Typical gangue minerals include calcite, quartz and barite [1]. Some sulphide gangue minerals such as pyrite, galena and sphalerite may also be present in fluorite ores. Selective flotation of fluorite from the gangue e.g. calcite and barite is challenging because all these minerals have similar physicochemical properties arising from Ca^{2+} surface cations. The Ca^{2+} cations react with the commonly used fatty acid collectors resulting in these minerals exhibiting similar flotation response translating to low-grade CaF_2 concentrates. The calcite and barite depressants also inhibit fluorite flotation, thus careful depressant selection is central to

selective fluorite flotation. The presence sulphidic gangue minerals in fluorite ores results in a CaF_2 concentrate with sulphur content higher than the market specification of 0.03%. It is therefore necessary to control the sulphidic gangue in fluorite flotation. Some fluorite processing plants are located in northern China which is characterised by long cold winters necessitating thermal heating of the ore slurry translating to high energy costs. Apart from proper selection of depressants, high-temperature pulp treatment has also been shown to improve the selectivity in fluorite flotation [2-4]. There is therefore a need to come up with customised flowsheets and efficient optimised reagent regimes for improved selectivity and reduced energy costs in fluorite flotation [4-6].

In this study, the role of gangue mineralogy on the flotation of 2 different fluorite ores was investigated. It was proposed that flowsheet and reagent regime selection in fluorite flotation depends on the type and proportion gangue minerals present in an ore. This paper presents results of batch scale flotation tests for 2 different fluorite ores sourced from different geographical locations. The effects of pulp temperature, reagent types and flowsheet on flotation of the 2 fluorite ores were systematically investigated in this study. Optimisation of different reagent regimes was achieved by varying reagent dosages in order to improve fluorite grade-recovery relationships.

Materials and Methods

Sample Preparation, Mineralogical and Chemical Analysis

2 fluorspar ores sourced from different geographical locations within Morocco and South Africa (thereafter referred to as A and B, respectively in this manuscript) were investigated in this study. The ores were crushed to minus 1.7mm for flotation tests using a jaw crusher. A rotary splitter was then used to divide the ores into 1 kg representative samples. The mineralogical analysis of the representative sized particles of the ores were conducted using a field emission gun Automated Quantitative Electron Scanning Microscopy (QEMSCAN). The particle mineral maps were produced using the Particle Map Analysis (PMA)

measuring mode, from which the bulk modal proportions of the minerals present, the liberation and association information of fluorine-bearing minerals were derived. The major elemental composition of the fluorite ores was determined using XRF method, which required the double Ca titration method for the removal of soluble Ca from carbonates followed by the determination of Ca associated with fluorine

Reagents

The chemical reagents used in this study are shown in

Table 1. Reagent selection was conducted in close consultation with various flotation reagent suppliers based on their database and experience on treatment of similar ore types. Flotinator 7243 is a mixture of laurylpolyglycolethercarboxylic acid (LCA) and nonylphenol polyglycol ether (NPE). A variety of gangue depressants were tested in this study based on the type of gangue minerals present in each ore (Section 3.1). All the reagents were dosed based on active content and standard tap water was used as the medium in all flotation experiments.

Table 1: List of reagents used in this study.

Reagent	Chemical Name / Formular	Use	Purity (%)	Targeted ore	Supplier
Flotisor 7243	Fatty acid	Fluorite collector	15-25 LCA; 5-15 NPE	A	Clariant
Sylfat FA 2	Tall oil fatty acid	Fluorite collector	100	B	Arizona Chemicals, USA
Sodium fluoride	NaF	Fluorite activator	100	A & B	Hyperion chemicals & consulting
Sodium amyl xanthate	C ₃ H ₅ NaOS ₂	Sulphide collector	99.9	B	Senmin
Sodium hydrosulphide	NaHS	Sulphide activator	75 NaHS; 3 Na ₂ S; 15 ppm Fe content	B	Axis house
Soda ash	Na ₂ CO ₃	pH modifier	100	A & B	Hyperion chemicals & consulting
Pionerra F250 -	Sodium lignin sulphonate	Barite & sulphide depressant	100	A & B	Hyperion chemicals & consulting
Tan XS	<i>Acacia mearnsii</i> extract, bisulfited	Calcite depressant	64	A & B	Bondtite (Pty) Limited
Sodium silicate	Na ₂ SiO ₃	Silica depressant	40	A & B	Hyperion chemicals & consulting

Batch Flotation Tests

The Denver D12 flotation machine with a volume of 2.5 L cell was used for the batch flotation testwork at an impeller speed of 1500 rpm. Milling tests were conducted on the ore to establish the milling time required to achieve targeted grinds for the 2 different ores (Section 3.2). The market's product particle size distribution (PSD) specification was 80% passing 65 μm and hence grinds coarser than 65 μm were investigated in this study. High chrome steel rods were used as grinding media and milling was conducted at 50% solids concentration in the mill. Batch flotation tests were conducted on 1 kg feed samples that were rod milled to a given grind. The milled slurry was conditioned in a Denver D12 flotation machine at an impeller speed of 1500 rpm and slurry density of 33% solids in the rougher and 18% in the cleaners. All flotation reagents were prepared at 1% strength with exception on the fatty acids, which were added neat. A given amount of depressant was added followed by the addition of a given amount of collector. Sodium carbonate was used as a pH modifier in the rougher, targeting a pH of 9.5. Pulp temperature was adjusted to a targeted value using a water bath. The concentrates and the tailings were dried separately. The dry mass of the concentrates and tailings were determined to calculate the recoveries. The concentrates were assayed for CaF_2 , CaCO_3 , SiO_2 and S using the techniques highlighted in Section 3.1. Fluorite grade-recovery curves were used as primary responses to compare the performances of different flowsheets and reagent regimes.

Results and Discussion

Mineralogical and Chemical Analysis

The head grade, mineralogical composition and the mineral phase proportions of ores A and B are shown in Table 2 and Figure 1. Liberation characteristics of both ores were determined at a grind of 80% passing 150 μm .

Table 2: Chemical analysis of the fluorspar ores A and B.

Ores	CaF ₂	SiO ₂	CaCO ₃	Fe	S	Ba
A	30.4	26.1	36.2	0.33	0.41	1.45
B	26.9	6.32	54.3	5.97	4.10	0.22

Figure 1: Bulk mineralogical analysis of fluorspar ores A and B.

It is clear from Table 2 and Figure 1 that the CaF₂ grades were relatively similar in both ores. However, there were significant differences in terms of the type and proportion of the gangue minerals present in both ores. Ore A had higher quartz and calcite contents compared to ore B. In fact, the quartz and calcite contents of ore A were approximately eleven times and twice those of ore B, respectively. On the other hand, ore B had higher pyrite and dolomite contents compared to ore A. It is clear that ore B had 30 times the pyrite content of ore A. The dolomite content in ore B was 13 times that in ore A. The differences in the mineralogical contents of the 2 ores are expected to affect flowsheet and reagent regime selection to process both ores.

Flowsheet Development

The development of suitable flowsheets and optimised reagent regimes for the processing of ores A and B was based on the ores' mineralogical characteristics. Preliminary reagent scouting tests showed that Flotinator 7243 and Arizona Sylfat FA2, both fatty acid collectors, produced superior metallurgical results for the processing of ore A and B, respectively. The results were not presented not only for the brevity of the manuscript but also because this paper only focussed on the role of gangue

mineralogy on flowsheet development for fluorite processing. Preliminary flotation testwork also showed that six cleaning stages were required to produce an acid grade CaF_2 product from both ores.

Flowsheet for Ore A

The mineralogical and chemical analysis results depicted in Table 2 and Figure 1, indicate that for ore A to be upgraded, quartz and calcite minerals are to be separated from the fluorite during flotation. Tannins have been shown to be strong calcite depressant [6,7] while sodium silicate is reported to be an effective silica depressant [8,9]. In terms of liberation characteristics at a grind of 80% passing 150 μm , 90% of the fluorite grains were fully liberated, with less than 15% of fluorite grains showing an intimate association with calcite and other silicate gangue minerals. Therefore, a grind of 80% passing 150 μm was assumed suitable to achieve adequate liberation of selective fluorite flotation. A simple flotation flowsheet shown in Figure 2 was proposed for processing ore A.

Figure 2: Flowsheet for the processing of ore A.

Flowsheet for Ore B

The beneficiation of ore B required the depression of pyrite, calcite and dolomite. Similar to ore A, Tannins and sodium silicate were used as calcite and silica depressants [6,7,8,9]. Lignin sulphonate is reported to be an effective pyrite depressant [10]. In terms of liberation characteristics at a grind of 80% passing 150 μm , 25% of fluorite grains were fully liberated with 75% of fluorite grains reporting as middlings and 42% fluorite being associated with major gangue. Because of the poor degree of liberation, ore B might require concentrate regrinding to liberate the fluorite grains as opposed to ore A. To determine the optimum grind for ore B, the effect of grind on the grade-recovery relationship in rougher flotation was investigated and the results are shown in Table 3.

Table 3: Effect of grind on CaF_2 grade-recovery relationship for ore B using Arizona Sylfat FA2 collector in rougher cells.

P_{80} grind (μm)	Mass pull (%)	CaF_2 grade (%)	CaF_2 recovery (%)
125	46.6	32.8	86.5
106	37.1	41.9	86.0
90	44.1	34.0	89.6
75	52.3	30.2	88.7

Table 3 shows that the rougher CaF_2 recoveries for P_{80} grinds of 125 μm and 106 μm were similar at 86% while for P_{80} of 90 μm and 75 μm the rougher CaF_2 recoveries were similar at 89%. The rougher CaF_2 grades decreased in the following order: $P_{80} = 106 \mu\text{m} > P_{80} = 90 \mu\text{m} > P_{80} = 125 \mu\text{m} > P_{80} = 75 \mu\text{m}$. Because it produced the highest CaF_2 grade at reasonably high CaF_2 recoveries, the 80% passing 106 μm grind was selected as the optimum grind for further flotation testwork with a view to improve metallurgical performance.

Different process routes were considered for the removal of the pyritic gangue in ore B. The first route was through the selective depression of the pyritic gangue using the simple flowsheet shown in

Figure 2. The second route was an upfront removal of the pyritic gangue using a pre-sulphide flotation cell as shown in Figure 3. The second route used NaHS as a sulphide activator [2,11] at a low dosage of 15 g/t and potassium amyl xanthate (PAX) as a sulphide collector [12] in a pre-sulphide flotation cell. A higher NaHS dosage would be detrimental as it would depress the pyrite. NaHS functions by either cleaning or sulphidising the pyrite surface and hence improving the pyrite floatability. The metallurgical performance of the 2 process routes was evaluated and the results are presented in Table 4. Table 4 shows that, although both process routes produced an acid grade CaF_2 product, the pre-sulphide flotation route produced 50% less sulphur content compared to the selective depression route. The pre-sulphide flotation route produced higher CaF_2 recovery and grade than the selective depression route. It is clear that pre-sulphide flotation route was the most effective means of removing the pyritic gangue from the fluorite ore and hence the flowsheet in Figure 3 was used for further optimisation tests.

Table 4: Comparison of the metallurgical performance different process routes in terms of pyrite removal using lignin sulphonate depressant at 170 g/t dosage for ore B.

Process route	Grade (%)		Recovery (%)
	CaF_2	S	CaF_2
No pre-sulphide float	96.8	0.14	75.1
Pre-sulphide float	97.0	0.07	78.9

Although the pre-sulphide flotation route was successful in reducing the pyritic gangue reporting to the CaF_2 concentrate, the sulphur content was still higher than the market specification of at most 0.03%. Therefore, optimisation tests were conducted to reduce the sulphur content in the CaF_2 concentrate.

Figure 3: Flowsheet for the processing of Ore B which include a pre-sulphide flotation stage, fluorite roughing and sequential cleaning.

Effect of Pulp Temperature

Figure 4 shows the effect of pulp temperature on the CaF_2 grade-recovery relationship for ore A using the Flotinator 7243 collector at 300 g/t dosage. The objective was to evaluate the affinity and the subsequent efficiency of the collector towards different minerals within the ore as a function of pulp temperature. Figure 4 shows that as the pulp temperature increases, the CaF_2 recovery increases while the CaF_2 grade decreases. It is clear from Figure 3 that although the CaF_2 recovery was low around 56%, the product grade met the market specification of 97% CaF_2 at 20°C. However, it was not possible to produce the acid-grade concentrate at 40°C. In order to investigate whether the observed results were ore-specific or not, the effect of pulp temperature was also investigated for ore B using a different fatty acid collector, Slyfat FA2 at 300 g/t dosage and the results are presented in Figure 5.

Figure 4: Effect of pulp temperature on the grade-recovery relationship for ore A.

The results in Figure 5 show that an acid grade concentrate with a grade of 97% CaF₂ can be attained at 75% and 85% recoveries using the Sylfat FA2 collector at 20°C and 40°C respectively. A further increase of the pulp temperature to 60°C resulted in significant increase in CaF₂ recovery, but at the expense of CaF₂ grade. It was therefore not possible to produce an acid-grade concentrate at 60°C using the Sylfat FA2 collector.

Figure 5: Effect of pulp temperature on CaF₂ grade-recovery relationship for ore B.

It has been observed from Figure 4 and Figure 5 that an increase in the pulp temperature resulted in increased CaF_2 recovery and reduced CaF_2 grade for both ores. Thus, the results are not ore-specific. Similar observations were made by [4] who showed that better fluorite selectivity in carbonate-fluorite ores is achievable at low temperatures. The same finding was made by [3] on their investigation on a fluorite ore from China using sodium naphthenate and salted copper sulphate as collector and depressant of phosphate gangue minerals respectively. The results presented in both Figure 4 and Figure 5 suggest that operating at lower temperatures would be more favourable to produce an acid grade fluorite product. The results therefore show that both Flotinator 7243 and Sylfat FA2 can be effectively used as collectors in the flotation of ore A and B respectively to produce acid grade CaF_2 concentrate at low pulp temperatures. Besides the benefit of increased selectivity, operating at low pulp temperatures would result in significant reduction in energy costs in fluorite flotation. This is especially true to most fluorite processing plants located in northern China which is characterised by long cold winters. In such plants, energy consumption is high due to heating of the ore slurry in flotation circuits for efficient separation. The use of the Flotinator 7243 and Sylfat FA2 collectors therefore eliminates the need for high-temperature pulp treatment and thus significant reduction in energy costs.

To understand the reason behind the loss of selectivity as pulp temperature increases, the behaviour of gangue minerals as a function of pulp temperature was investigated and the results are presented in

Table 5.

Table 5 shows that the calcite contamination increased with increasing pulp temperature. The increase in CaF_2 recoveries with increasing pulp temperature could be due to an increase in the hydrophobicity and subsequent floatability of CaF_2 as pulp temperature increases. This could be a result of improved dispersion of the collector throughout the pulp at high pulp temperatures.

Table 5: Effect of temperature on mass pull and gangue (calcite) contamination

Temperature (°C)	Mass Pull (%)	Grade (%)		CaF ₂ recovery (%)
		CaF ₂	CaCO ₃	
20	11.8	97.4	1.34	69.5
40	12.9	97.8	2.63	65.4
60	19.1	80.3	10.3	76.9

Improved collector dispersion and increased rate of mineral-collector interactions at high temperatures may promote the unselective adsorption of the fatty acid collector onto the gangue minerals. This renders the gangue minerals floatable and hence the observed increase in gangue dilution of the CaF₂ concentrate as pulp temperature increases. A similar finding was made by [13] in ilmenite flotation where they observed the improved floatability of feldspar and biotite gangue minerals as pulp temperature was increased resulting in reduced low grade ilmenite concentrates.

Effect of Fluorite Activation on Fluorite Flotation

The addition of sodium fluoride, NaF as a fluorite activator on the flotation performance of both ores A and B was investigated in the rougher flotation cell and the results are shown in Table 6. It is clear from Table 6 that increasing NaF dosage from 0 to 500 g/t resulted in a slight increase in the recovery of CaF₂ but significant increase in the concentrate grade for ore A. In fact, the concentrate grade was increased by more than 12%. The significant increase in CaF₂ grade was accompanied by around 50% decrease in silica and calcite gangue content. However, a further 50% increase in the NaF dosage resulted in a 3% drop in the CaF₂ grade. This was clearly due to the increase in the recovery of gangue at high NaF dosages.

It is also clear from Table 6 that CaF₂ recovery dropped by almost 50% when NaF was added to the roughers for ore B. Furthermore, gangue content increased with the addition of NaF.

This shows that the use of NaF at 500g/t dosage had a detrimental effect on fluorite recovery from ore B.

Table 6: Effect of fluorite activation using NaF on CaF_2 grade and recovery for ore A and B.

Ore type	NaF dosages (g/t)	Mass pull (%)	Grade (%)			CaF_2 Recovery (%)
			CaF_2	SiO_2	CaCO_3	
	0	33.0	84.0	2.46	1.42	83.0
A	500	29.2	96.4	1.41	0.75	85.0
	750	31.0	93.8	2.99	1.30	86.0
	0	22	95	0.32	2.29	80.6
B	500	14	93	0.84	3.23	48.0

The increase in the CaF_2 grade with increasing NaF dosage observed for ore A is consistent with the findings made by [4] who concluded that NaF improved fluorite selectivity in the rougher cells. [4] proposed that the NaF and collector interact forming fluorine-bearing associates which have a higher affinity for fluorite than gangue minerals, e.g. carbonates and sulphates. They also suggested that fluorite activation is a result of the restructuring of the fluorite surface layer under the influence of the excess F^- ions generated from the NaF addition. Both mechanisms should result in increased fluorite recovery and selectivity. However, the results presented in Table 6 suggest that there was an optimum dosage (500 g/t NaF) at which the CaF_2 grade was maximum and gangue contamination was minimum for ore A.

For ore B, the CaF_2 grade just dropped by addition of 500 g/t of NaF. The results seem to suggest that the 500 g/t NaF dosage was already higher the optimum NaF dosage. It is therefore recommended that lower NaF dosages be investigated to establish the optimum NaF dosage that would give the best metallurgical benefits in terms of CaF_2 grade and recovery for ore B.

At high NaF dosages, the excess fluorine-bearing associates formed from the interaction between the excess NaF and collector may unselectively adsorb onto the gangue minerals. Thus the gangue minerals become floatable, hence the observed increase in silica and calcite contamination. Neutralisation or

passivation of the Ca sites on the fluorite mineral surface by excess F^- may also occur, such that there are no longer any Ca sites available on the fluorite mineral surface to bond with the collector on the fluorite surface, hence the loss in CaF_2 recovery at high NaF dosages.

Effect of Sodium Silicate Dosage for ore A

The effect of adding sodium silicate as a silicate depressant in an attempt to reduce silica content to below 1% in the concentrate was investigated in the rougher flotation cell and the results are shown in

Table 7. It is clear from

Table 7 that only a slight improvement in silica depression was achieved by increasing sodium silicate dosage from 0 – 310 g/t. A further increase in the sodium silicate dosage to 390 g/t resulted in the targeted silica contamination of the less than 1% in the concentrate. However, this this was accompanied by significant loss in CaF_2 recovery. The CaF_2 recovery loss at a high sodium silicate dosage could be attributed to both reduced mass pull and the depression of the fluorite grains that are associated with silica gangue minerals as revealed by the mineralogical analysis (

Table 8). The lower sodium silicate dosage was therefore not strong enough to depress the silica associated with the fluorite particles. Mineral association data are derived from shared boundaries amongst the identified mineral grains, therefore the higher the associated percentage is, the greater the degree of boundary-sharing between mineral species. In

Table 8 it is clear that there exists some fluorite association with silicate minerals such as calcite, dolomite, pyroxene, K-feldspar and quartz which ultimately resulted in CaF_2 recovery loss when the depressant dosage was increased. This result indicate that there is an opportunity to explore other silicate depressants in an attempt to maximise the CaF_2 recovery to the product.

Table 7: Effect of sodium silicate on CaF_2 grade and recovery.

Na ₂ SiO ₃ dosage (g/t)	Mass pull (%)	Grade (%)			CaF ₂ Recovery (%)
		CaF ₂	SiO ₂	CaCO ₃	

0	29.2	96.4	1.63	1.49	83.0
310	28.2	96.5	1.41	0.75	85.0
390	24.5	97.4	0.92	0.60	73.2

Table 8: Mineral associations between fluorite and gangue minerals.

Mineral name	Fluorite	Calcite	Dolomite
Free surface	66.23	60.69	13.24
Fluorite	0.00	14.98	2.46
Pyrite	0.02	0.04	0.01
Barite	0.10	0.01	0.02
Pyroxene	2.79	2.41	0.89
K-Feldspar	0.15	0.18	0.03
Biotite	0.10	0.11	0.03
Quartz	0.83	0.76	0.27
Fe oxides	0.29	0.04	0.04
Calcite	28.22	0.00	82.93
Dolomite	1.16	20.69	0.00
Others	0.10	0.10	0.08

Effect of Concentrate Regrind for Ore B

The results so far have demonstrated that it is possible to produce an acid-grade product with at least 96% CaF_2 . However, the S content in the CaF_2 concentrate was very high above the market specification of 0.03%. The high S content could be attributed to the association of fluorite grains with sulphide minerals as shown from the mineralogical analysis of the CaF_2 concentrate presented in

Table 11.

Table 11 shows that 24% of the sulphides were associated with fluorite grains and hence the effect of concentrate regrinding on the sulphur content in the CaF_2 concentrate was investigated and the results are shown in Figure 6 and Table 9.

To avoid grinding finer than the market's product PSD specification of 80% passing $65\mu\text{m}$, a milling curve was constructed which showed that the regrind time of at 8 minutes produced a product with a PSD coarser than a P_{80} of $65\mu\text{m}$. The milling curve showed that a regrind time of 1 minute was required to achieve a P_{80} of $90\mu\text{m}$. 2 cleaner concentrates were therefore independently ground for 1 and 2 minutes. Figure 6 shows that concentrate regrinding reduced both the CaF_2 recoveries and grades. The drop in CaF_2 recoveries could be due to the slower floating finer particles generated during the concentrate regrind. The drop in the grade of the CaF_2 concentrate grade could be due to increased liberation of floatable gangue such as calcite. The results in Table 9 also indicate that concentrate regrinding resulted in reduced S content reporting to the CaF_2 concentrate. However, the S content was still above the market specification of 0.03%. Overall, concentrate regrinding had a detrimental effect of concentrate dilution by calcite as well as reduced CaF_2 recovery. It was also observed that with longer regrinding time, the total sulphur content increased. It is therefore clear that the processing of ore B without regrind was still the best, though sulphur content was still off-spec.

Figure 6: Effect of concentrate regrind on CaF₂ grade and recovery.

Table 9: Effect of concentrate regrind on CaF₂ grade and recovery.

Regrind time (minutes)	Grade (%)			CaF ₂ Recovery (%)
	CaF ₂	CaCO ₃	S	
0 (no regrind)	97.2	3.51	0.07	78.9
1	93.4	3.72	0.06	77.6
2	91.3	4.26	0.59	72.4

Effect of Lignin Sulphonate (Pionerra F250) Dosage on Sulphur Reduction for Ore B

Further flotation testwork was conducted using lignin sulphonate (Pionerra F250) as a sulphide depressant with no regrind with a view to reduce the S content to the industry specification of 0.03%. The depressant dosages were varied from 170 – 210 g/t and the results are presented in

Table 10. It is clear from the

Table 10 that an increase in lignin sulphonate dosage resulted in a decrease in the total sulphur in the CaF₂ concentrate from 0.07% to 0.02%. Therefore the acid-grade concentrate specifications were met in terms of both CaF₂ and S grades although this was accompanied by a 7% loss in CaF₂ recovery. It can be concluded that the stage addition sulphide depressants in the rougher and cleaning stages in the processing of fluorite ores having high sulphur content is necessary to control the sulphur content in the concentrate.

Table 10: Effect of lignin sulphonate depressant on S grade as well as CaF₂ grade and recovery.

Lignin-sulphonate (g/t)	Mass pull (%)	Grade (%)			CaF ₂ Recovery (%)
		CaF ₂	SiO ₂	S	
170	23	97.1	0.25	0.07	78.9
210	20	96.5	0.80	0.02	72.0

The observed loss in CaF₂ recovery could be attributed to the depression of the sulphide minerals that are associated with the

fluorite. To investigate this, mineralogical analysis was conducted on the concentrate to further understand the association of the minerals present in the ore and the results are shown in

Table 11.

Table 11 shows that 37% of the sulphides were associated with fluorite and carbonates while 7% of the sulphides were associated with other minerals. This observation shows that CaF_2 recovery loss was inevitable if the S content in the final concentrate is to be reduced using a sulphide depressant.

Table 11: Fluorite concentrate sulphide mineral association

Mineral	Sulphide mass %
Matrix	51.2
Serpentine	0.22
Pyroxene	0.63
Feldspar	0.10
Mica	0.47
Quartz	0.79
Fe oxides	2.88
Fluorite	23.7
Carbonates	13.1
Apatite	0.10
Others	6.80
Total	100

Conclusions

This study investigated the role of gangue mineralogy on flowsheet and reagent regime selection on the processing of 2

different fluorite ores. One ore had higher quartz and calcite contents while the other had higher pyrite and dolomite contents. Customised flowsheets and efficiently optimised reagent regimes were investigated for the optimum production of acid-grade fluorite for each ore by the froth flotation process. An increase in pulp temperature resulted in increased CaF_2 recovery but decreased CaF_2 grade for both ores. The results therefore show that the fatty acid collectors can be effectively used in the fluorite flotation to produce acid-grade CaF_2 concentrate at ambient pulp temperatures. High selectivity at low pulp temperatures eliminates the need for high-temperature pulp treatment and thus translates to significant reduction in thermal energy costs.

This study showed that gangue mineralogy plays a very important role in flowsheet and reagent regime selection on the processing of the different fluorite ores. Although an acid-grade CaF_2 concentrate could be obtained from both ores, the flowsheets and reagent regimes were markedly different. Multiple stages of cleaning were required for improved selectivity in the flotation of both ores. Production of an acid-grade CaF_2 product from a high quartz and calcite ore was achieved by employing a simple rougher-multiple cleaner flotation circuit using tannin and sodium silicate as calcite and quartz depressants respectively. On the other hand, the production of an acid-grade CaF_2 product flotation of the pyritic ore required a pre-sulphide flotation stage for upfront sulphur removal and a sulphide depressant during cleaning to meet the market specification with regards to sulphur content. The results showed that an understanding of the gangue mineralogy is key to process optimisation for acid grade CaF_2 production.

References

1. Magotra R, Namga S, Singh P, Arora N, Srivastava PK. A new classification scheme of fluorite deposits. *International Journal of Geosciences*. 2017; 8: 599-610.
2. Crozier RD. *Flotation, Theory, Reagents and Ore Testing*. Oxford: Pergamon. 1992.

3. Zhang Y, Song S. Beneficiation of fluorite by flotation in a new chemical scheme. *Minerals Engineering*. 2003; 16: 597-600.
4. Kienko LA, Samatova LA, Voronova OV, Komdrat'ev SA. Lower temperature flotation of carbonate-fluorite ores. *Journal of Mining Science*. 2010; 46: 317-323.
5. Zhou Q, Lu S. Acidized sodium silicate - an effective modifier in fluorite flotation. *Minerals Engineering*. 1992; 5: 435-444.
6. Ren Z, Yu F, Gao H, Chen Z, Peng Y, et al. Selective separation of fluorite, barite and calcite with valonea extract and sodium fluorosilicate as depressants. *Minerals*. 2017; 7: 1- 24.
7. Rutledge J, Anderson CG. Tannins in mineral processing and extractive metallurgy. *Metals*. 2015; 5: 1520-1542.
8. Zhou W, Moreno J, Torres R, Valle H, Song S. Flotation of fluorite from ores by using acidized water glass as depressant. *Minerals Engineering*. 2013; 45: 142-145.
9. Zhang G, Gao Y, Chen W, Liu D. The role of water glass in the flotation separation of fine fluorite from fine quartz. *Minerals*. 2017; 157: 1-14.
10. Liu RQ, Sun W, Hu YH, Wang DZ. Effect of organic depressant lignosulfonate calcium on separation of chalcopyrite from pyrite. *Journal of Central South University of Technology*. 2009; 16: 753-757.
11. Kongolo K, Kipoka M, Minanga K, Mpoyo M. Improving efficiency of oxide-cobalt ores flotation by combination of sulphidisers. *Minerals Engineering*. 2003; 16: 1023-1026.
12. Taguta J, O'Connor CT, McFadzean B. The effect of alkyl chain length and ligand type of the enthalpy of adsorption and floatability of sulphide minerals. *Minerals Engineering*. 2017; 110: 145-152.
13. Parkins EJ. Effect of temperature on the conditioning and flotation of an ilmenite ore. PhD Thesis, Mineral Technology Department. Royal School of Mines, Imperial College. London University. 1975.